




Stenrix™ Grooved 13/3

Product by Timberix™



Trademark and 2026 ©

Stenrix™ panels reduce echoes by trapping and diffusing sound across surface geometry and perforations. Sound passing through perforations is absorbed by an acoustic substrate such as fibreglass or mineral wool, reducing reverberation. Smaller patterns attenuate high frequencies, while larger formats help control lower frequencies.



Technical Specifications

Structure	Core, Surface Finish, Backing
Core	E1 MDF, FR MDF, Black MDF, MgO
Surface Finish	Natural Stone
Standard Dimension	128mm x 2420mm
Standard Thickness	15mm
Slat Width	13mm
Groove Width	3mm
Formaldehyde Emission	EN 13986 = E1
Fire Classification	EN 13501-1 = Class B s1, d0 ASTM E84-23 = Class A
Acoustic Test Configuration	Grooved 13/3 with Insulation
Weighted Absorption (aw)	ISO 11654 = 0.95, Class A
Noise Reduction Coefficient (NRC)	ASTM C423 = 0.95